

# PRODUCT DATA SHEET Modi-Torch 5.5kg Capsheet

Characteristic	Test Method	Result
Roll length*	BS EN 1848-1	8m
Roll width**	BS EN 1848-1	1m
Weight***	BS EN 1849-1	42kg
Watertightness	BS EN 1928 method a.	PASS
Tensile strength:****	BS EN 12311-1	
Longitudinal		1100 N/50mm
Transverse		1000 N/50mm
Elongation at maximum load:	BS EN 12311-1	
Longitudinal		26%
Transverse		38%
Resistance to tearing:****	BS EN 12310-1	
Longitudinal		225 N
Transverse		180 N
Straightness	BS EN 1848-1	PASS
Visible Defects	BS EN 1850-1	PASS
Cold Bend Flexibility	BS EN 1109	-5°C
Flow Resitance at Elevated	BS EN 1110	90°c
Temperature		
External Fire Performance	BS EN 13501-5	Froor(t4)
Reaction to Fire	BS EN 13501-1	F

<sup>\*</sup>tolerance of >150mm

## PRODUCT COMPLIANCE

The product complies with BS EN 13707:2004+A2:2009 and CPR 305/2011/EU. It is CE marked under the Factory Production Control Certificate number 0836-CPR-13/F049.

### **STANDARD PRODUCT**

Standard length and weigh is:

Modi-Torch 5.5kg Capsheet 8m 42kg 25 rolls per pallet

## Mineral Colours Available: Green, Red, Blue Grey, Mixed Brown, Charcoal.

Note: Field trials have indicated significant differences in the surface temperature between mineral finishes. Charcoal on average retained heat upto 10°c higher than mixed brown. For superior UV protection the lighter mineral finishes have proved more effective.

\*Rose Roofing is continually investigating methods of improving both quality and performance and therefore reserves the right to change specifications and product composition without prior notice.

**Date of Issue: September 2019** 

#### **PRODUCT USE**

Intended for use as the intermediate layer and final capsheet in a traditional bituminous built-up flat roof system.

#### COMPOSITION AND MANUFACTURE

The base carrier consists of a high strength polyester sheet that is saturated then coated both sides with SBS modified bitumen. The coated material is finished with either a fine sand upper surface, or a coarse mineral upper surface to aid UV protection and a thin HDPE film lower surface that melts during installation. The membrane is cut to roll length, taped and packaged according to specification and customer requirement.

#### INSTALLATION

Prior to setting the specification for a torch applied built up roof system Rose Roofing recommend considering the use of a hot bonded or mechanically fixed underlay / preperation layer to avoid the fire risks associated with direct torching onto combustible substrates. Rose Roofing also recommend that a thorough and comprehensive review assessing any combustion risk of the areas surrounding the detailing be carried out before torch applying materials to such areas.

Rose Roofing's Modi-Torch capsheets are applied by torch-on application using a standard roofer's torch. The membrane should be heated carefully ensuring the film on the underside melts completely and there is a constant steady pool of hot bitumen across the whole sheet. Side laps must be a minimum of 75mm on sand finished products, and follow the manufactured mineral free selvedge on mineral capsheets. End laps should be a minimum of 150mm. When the Underlays and Capsheets are applied they should be offset on sides and ends over the underlay joints to prevent build up of overlaps, and ensure good bond strength evenly throughout the roof system.

#### STORAGE & HANDLING

Do not drag rolls across rough surfaces, they should be lifted. They should be stood on their end on a dry surface. If using pallets do not stack more than 2 high. Avoid mechanical damage and wet storage conditions. During colder periods it is recommended that rolls are stored at a temperature above 10°c for 24 hours prior to use. Hydrocarbon solvent based products will have a damaging effect upon these membranes, care must be taken to prevent contact with each other.

<sup>\*\*</sup>tolerance of +/-1.5% \*\*\*tolerance of +/-7.5% \*\*\*\*tolerance of +/-15%